

PROPERTY INFORMATION

KOLON INDUSTRIES INC

KOPA[®]

POLYAMIDE-66 RESIN

KN3322VO

FLAME RETARDED

PROPERTY	ASTM METHOD	UNIT			VALUE			
MISCELLANEOUS								
SPECIFIC GRAVITY	D792				1.29			
WATER ABSORPTION	D570	%			0.6			
MOLD SHRINKAGE	D955	%			1.3			
THERMAL								
MELTING POINT	D789	°C	°F	255	491			
HEAT DEFLECTION TEMPERATURE	D648							
4.6kg.f/cm ³ (0.46 Mpa)		°C	°F	235	455			
18.6kg.f/cm ³ (1.82 Mpa)		°C	°F	105	221			
COEFFICIENT OF LINEAR THERMAL EXPANSION	D696	10 ⁻⁴ cm/cm/°C			0.7			
FLAMMABILITY	UL94				HB			
MECHANICAL								
TENSILE STRENGTH	73°F (23°C)	D638	kgf/cm ²	Mpa	psi	820	80	11,660
TENSILE ELOGATION	73°F (23°C)	D638	%			15		
FLEXURAL STRENGTH	73°F (23°C)	D790	kgf/cm ²	Mpa	psi	1,350	132	19,197
FLEXURAL MODULUS	73°F (23°C)	D790	kgf/cm ²	Mpa	psi	32,000	3,138	455,029
IZOD NOTCHED IMPACT STRENGTH		D256	kgcm/cm	J/m	ft.lb/in	5	49	0.92
HARDNESS ROCKWELL	R SCALE	D785	g/cc			120		
ELECTRICAL								
ARC RESISTANCE	D495	sec			125			
DIELECTRIC CONSTANT	D150	10 ⁶ Hz			3.4			
DIELECTRIC STRENGTH	D149	KV/mm			20			

The information provided on our present state of knowledge and is estimated by Kolon Industries Inc. The listed values should be used for referential purposes only. This information should not be used as guaranteed specification limits. Kolon Industries Inc assumes no warranty, no obligations or liability of, express or implied as to the accuracy or completeness thereof, or any other nature regarding designs, products, or information may be used without infringing the intellectual property rights of others. All such advice is given and accepted at buyer's risk.



333 Enterprise Parkway • Lake Zurich • IL • 60047 • USA
 Phone: 1-847-550-5556 Fax: 1-847-550-5557
 Email: MaxHahn21@hotmail.com