

PROPERTY INFORMATION

KOLON INDUSTRIES INC

KOPA®

POLYAMIDE-66 RESIN

KN333G45

G/F REINFORCED GRADE

PROPERTY	ASTM METHOD	UNIT			VALUE			
MISCELLANEOUS								
SPECIFIC GRAVITY	D792				1.5			
WATER ABSORPTION	D570	%			0.3			
MOLD SHRINKAGE	D955	%			0.3			
THERMAL								
MELTING POINT	D789	°C	°F	255	491			
HEAT DISTORTION TEMPERATURE	D648							
4.6kg.f/cm ² (0.46 Mpa)		°C	°F	252	486			
18.6kg.f/cm ² (1.82 Mpa)		°C	°F	250	482			
COEFFICIENT OF LINEAR THERMAL EXPANSION	D696	10 ⁻⁴ cm/cm/°C			0.2			
FLAMMABILITY	UL94				HB			
MECHANICAL								
TENSILE STRENGTH	73°F (23°C)	D638	kgf/cm ²	Mpa	psi	2,200	216	31,283
TENSILE ELOGATION	73°F (23°C)	D638	%			5		
FLEXURAL STRENGTH	73°F (23°C)	D790	kgf/cm ²	Mpa	psi	3,400	333	48,347
FLEXURAL MODULUS	73°F (23°C)	D790	kgf/cm ²	Mpa	psi	123,000	12,062	1,749,016
IZOD NOTCHED IMPACT STRENGTH		D256	kgcm/cm	J/m	ft.lb/in	12.0	118	2.21
HARDNESS ROCKWELL	R SCALE	D785	g/cc			125		
ELECTRICAL								
ARC RESISTANCE	D495	sec			135			
DIELECTRIC CONSTANT	D150	10 ⁶ Hz			3.6			
DIELECTRIC STRENGTH	D149	KV/mm			21			

The information provided on our present state of knowledge and is estimated by Kolon Industries Inc. The listed values should be used for referential purposed only. This information should not be used as guranteed specification limits.

Kolon industries Inc assumes no warranty, no obligations or liability of, express or implied aas to the accuracy or compeltteness thereof, or any other nature regarding designs, products, or information may be used without infringing the intellectual property rights of others. All such advice is given and accepted at buyer's risk.

API-KOLON
Engineering Plastics

333 Enterprise Parkway • Lake Zurich • IL • 60047 • USA

Phone: 1-847-550-5556 Fax: 1-847-550-5557

Email: MaxHahn21@hotmail.com