

PROPERTY INFORMATION

KOLON INDUSTRIES INC

KOPET®
PET RESIN

KP133G30
G/F REINFORCED GRADE

PROPERTY	ASTM METHOD	UNIT			VALUE			
MISCELLANEOUS								
SPECIFIC GRAVITY	D792				1.59			
WATER ABSORPTION	D570	%			0.05			
MOLD SHRINKAGE	D955	%			0.3			
THERMAL								
MELTING POINT	D789	°C	°F	254	489			
HEAT DISTORTION TEMPERATURE 4.6kg.f/cm ³ (0.46 Mpa)	D648	°C	°F	224	435			
COEFFICIENT OF LINEAR THERMAL EXPANSION	D696	10 ⁻⁴ cm/cm/°C			0.3			
FLAMMABILITY	UL94				HB			
MECHANICAL								
TENSILE STRENGTH	73°F (23°C)	D638	kgf/cm ²	Mpa	psi	1,300	127	18,486
TENSILE ELOGATION	73°F (23°C)	D638	%			5		
FLEXURAL STRENGTH	73°F (23°C)	D790	kgf/cm ²	Mpa	psi	2,100	206	29,861
FLEXURAL MODULUS	73°F (23°C)	D790	kgf/cm ²	Mpa	psi	85,000	8,336	1,208,670
IZOD NOTCHED IMPACT STRENGTH		D256	kgcm/cm	J/m	ft.lb/in	7.0	69	1.29
HARDNESS ROCKWELL	R SCALE	D785	g/cc			120		
ELECTRICAL								
ARC RESISTANCE	D495	sec			120			
DIELECTRIC CONSTANT	D150	10 ⁶ Hz			3.5			
DIELECTRIC STRENGTH	D149	KV/mm			20			

The information provided on our present state of knowledge and is estimated by Kolon Industries Inc. The listed values should be used for referential purposes only. This information should not be used as guaranteed specification limits.

Kolon industries Inc assumes no warranty, no obligations or liability of, express or implied as to the accuracy or completeness thereof, or any other nature regarding designs, products, or information may be used without infringing the intellectual property rights of others. All such advice is given and accepted at buyer's risk.

API-KOLON
Engineering Plastics

333 Enterprise Parkway • Lake Zurich • IL • 60047 • USA

Phone: 1-847-550-5556 Fax: 1-847-550-5557

Email: MaxHahn21@hotmail.com