

# THE TECHNICAL DATA SHEET

## ELLAS K-787A

### Physical Properties

Item	ASTM Method	Unit	Result/Remark
Specific Gravity	D 792		1.20
Hardness	D 2240	Shore A	87
100% Tensile Stress	D 412	Kgf/cm <sup>2</sup>	87
Tensile Strenght	D 412	Kgf/cm	470
Elogation	D 412	%	500
Tear Strenght	D 624	Kgf/cm	100

\*These are typical values and should not be used for establishing specifications.

### Applications: Calendar: FILM PVC Blend

### Injection Molding Temperature (°C)

C1	C2	C3	Nozzle
150 – 170	175 – 185	180 – 190	185 – 195

### Extrusion Molding Temperature (°C)

C1	C2	C3	C4	Head	Die
155 – 175	170 – 180	170 – 190	185 – 195	190 – 200	185 – 195

\* These recommended processing conditions can be varied on your machine design conditions.

\* Please dry and use TPU before processing it.

\* If you have any trouble in processing it, contact us.

**API-KOLON**  
Engineering Plastics

333 Enterprise Parkway · Lake Zurich · IL · 60047 · USA  
Telephone: 847-550-5556 Fax: 847550-5557  
E-mail: MaxHahn21@hotmail.com