

KN 120

Polyamide 6 base resin, Super bright, which can be used for both a raw material for compounding and monofilament extruded.

TEST ITEM	TEST METHOD	UNIT	VALUE
Moisture Content	KARL FISHER	%	below 0.08
Relative Viscosity	Sulfuric acid(96%)	-	2.82±0.03
Monomer content	-	%	below 1.0
TiO ₂ content	-	%	-
Chip Size	-	-	φ 1.55 X L1.92

Remark: The information provided in this data sheet is based on Kolon's knowledge and test method, therefore it can not be used as guaranteed specification limits.