

## PROPERTY INFORMATION

KOLON INDUSTRIES INC

# KOPA<sup>®</sup>

POLYAMIDE-6 RESIN

# KN132G30VO

FLAME RETARDANT WITH G/F GRADE

PROPERTY	ASTM METHOD	UNIT			VALUE			
<b>MISCELLANEOUS</b>								
SPECIFIC GRAVITY	D792				1.55			
WATER ABSORPTION	D570	%			0.7			
MOLD SHRINKAGE	D955	%			0.5			
<b>THERMAL</b>								
MELTING POINT	D789	°C	°F	220	428			
HEAT DISTORTION TEMPERATURE	D648							
4.6kg.f/cm <sup>3</sup> (0.46 Mpa)		°C	°F	210	410			
18.6kg.f/cm <sup>3</sup> (1.82 Mpa)		°C	°F	200	392			
COEFFICIENT OF LINEAR THERMAL EXPANSION	D696	10 <sup>-4</sup> cm/cm/°C			0.3			
FLAMMABILITY	UL94				V-O			
<b>MECHANICAL</b>								
TENSILE STRENGTH	73°F (23 °C)	D638	kgf/cm <sup>2</sup>	Mpa	psi	1,700	167	24,173
TENSILE ELOGATION	73°F (23 °C)	D638	%			5		
FLEXURAL STRENGTH	73°F (23 °C)	D790	kgf/cm <sup>2</sup>	Mpa	psi	2,600	255	36,971
FLEXURAL MODULUS	73°F (23 °C)	D790	kgf/cm <sup>2</sup>	Mpa	psi	85,000	8,336	1,208,670
IZOD NOTCHED IMPACT STRENGTH		D256	kgcm/cm	J/m	ft.lb/in	10.0	98	1.84
HARDNESS ROCKWELL	R SCALE	D785	g/cc			120		
<b>ELECTRICAL</b>								
ARC RESISTANCE	D495	sec			130			
DIELECTRIC CONSTANT	D150	10 <sup>6</sup> Hz			3.8			
DIELECTRIC STRENGTH	D149	KV/mm			21			

The information provided on our present state of knowledge and is estimated by Kolon Industries Inc. The listed values should be used for referential purposed only. This information should not be used as guaranteed specification limits. Kolon industries Inc assumes no warranty, no obligations or liability of, express or implied aas to the accuracy or compeltensness thereof, or any other nature regarding designs, products, or information may be used without infringing the intellectual property rights of others All such advice is given and accepted at buyer's risk.

**API- KOLON**  
Engineering Plastics

1121 Rose Road • Lake Zurich • IL • 60047 • USA  
Phone: 1(847)550-5556 Fax: 1(847)550-5557  
Email: MaxHahn21@hotmail.com