

KN 138D

Polyamide 6 base resin, Semidull, Yarn application.

TEST ITEM	TEST METHOD	UNIT	VALUE
Moisture Content	KARL FISHER	%	below 0.08
Relative Viscosity	Sulfuric acid(96%)	-	2.65±0.04
Monomer content	-	%	below 0.8
TiO ₂ content	-	%	0.31±0.04
Chip Size	-	-	φ 1.7 X L3.0

Remark: The information provided in this data sheet is based on Kolon's knowledge and test method, therefore it can not be used as guaranteed specification limits.

API-KOLON
Engineering Plastics

333 Enterprise Parkway • Lake Zurich • IL • 60047 • USA

Phone: 1-847-550-5556 Fax: 1-847-550-5557

Email: MaxHahn21@hotmail.com