

KN 190- 1

Polyamide 6 base resin, High viscosity, extrusion for film,
which can be used for injection purpose also

TEST ITEM	TEST METHOD	UNIT	VALUE
Moisture Content	KARL FISHER	%	below 0.08
Relative Viscosity	Sulfuric acid(96%)	-	3.55±0.03
Monomer content		%	below 1.0
TiO ₂ content		%	-
Chip Size		-	φ 2.0 X L2.0

Remark: The information provided in this data sheet is based on Kolon's knowledge and test method,
therefore it can not be used as guaranteed specification limits.

API-KOLON
Engineering Plastics

333 Enterprise Parkway • Lake Zurich • IL • 60047 • USA
Phone: 1-847-550-5556 Fax: 1-847-550-5557
Email: MaxHahn21@hotmail.com