

# PROPERTY INFORMATION

KOLON INDUSTRIES INC

# KOPA<sup>®</sup>

POLYAMIDE-66 RESIN

# KN333HB440BL

MULTI REINFORCED GRADE

PROPERTY	ASTM METHOD	UNIT			VALUE			
<b>MISCELLANEOUS</b>								
SPECIFIC GRAVITY	D792				1.42			
WATER ABSORPTION	D570	%			0.4			
MOLD SHRINKAGE	D955	%			0.3			
<b>THERMAL</b>								
MELTING POINT	D789	°C	°F	255	491			
HEAT DISTORTION TEMPERATURE	D648							
4.6kg.f/cm <sup>3</sup> (0.46 Mpa)		°C	°F	245	473			
18.6kg.f/cm <sup>3</sup> (1.82 Mpa)		°C	°F	230	446			
COEFFICIENT OF LINEAR THERMAL EXPANSION	D696	10 <sup>-4</sup> cm/cm/°C			0.3			
FLAMMABILITY	UL94				HB			
<b>MECHANICAL</b>								
TENSILE STRENGTH	73°F (23 °C)	D638	kgf/cm <sup>2</sup>	Mpa	psi	1,400	137	19,907
TENSILE ELOGATION	73°F (23 °C)	D638	%			5.0		
FLEXURAL STRENGTH	73°F (23 °C)	D790	kgf/cm <sup>2</sup>	Mpa	psi	2,100	206	29,861
FLEXURAL MODULUS	73°F (23 °C)	D790	kgf/cm <sup>2</sup>	Mpa	psi	91,000	8,924	1,293,987
IZOD NOTCHED IMPACT STRENGTH		D256	kgcm/cm	J/m	ft.lb/in	6.0	58.8	1.1
HARDNESS ROCKWELL	R SCALE	D785	g/cc			120		
<b>ELECTRICAL</b>								
ARC RESISTANCE	D495	sec			135			
DIELECTRIC CONSTANT	D150	10 <sup>6</sup> Hz			3.4			
DIELECTRIC STRENGTH	D149	KV/mm			21			

The information provided on our present state of knowledge and is estimated by Kolon Industries Inc. The listed values should be used for referential purposed only. This information should not be used as guranteed specification limits. Kolon industries Inc assumes no warranty, no obligations or liability of, express or implied aas to the accuracy or compeltteness thereof, or any other nature regarding designs, products, or information may be used without infringing the intellectual property rights of others. All such advice is given and accepted at buyer's risk.



333 Enterprise Parkway • Lake Zurich • IL • 60047 • USA  
Phone: 1-847-550-5556 Fax: 1-847-550-5557  
Email: MaxHahn21@hotmail.com