

PROPERTY INFORMATION

KOLON INDUSTRIES INC

KOPA®

POLYAMIDE-66 RESIN

KN333MS

LOW FRICTION GRADE

PROPERTY	ASTM METHOD	UNIT			VALUE			
MISCELLANEOUS								
SPECIFIC GRAVITY	D792				1.16			
WATER ABSORPTION	D570	%			1			
MOLD SHRINKAGE	D955	%			1.0			
THERMAL								
MELTING POINT	D789	°C	°F		255	491		
HEAT DISTORTION TEMPERATURE	D648							
4.6kg.f/cm ³ (0.46 Mpa)		°C	°F		230	446		
18.6kg.f/cm ³ (1.82 Mpa)		°C	°F		210	410		
COEFFICIENT OF LINEAR THERMAL EXPANSION	D696	10 ⁻⁴ cm/cm/°C			0.7			
FLAMMABILITY	UL94				HB			
MECHANICAL								
TENSILE STRENGTH	73°F (23°C)	D638	kgf/cm ²	Mpa	psi	950	93	13,509
TENSILE ELOGATION	73°F (23°C)	D638	%			10.0		
FLEXURAL STRENGTH	73°F (23°C)	D790	kgf/cm ²	Mpa	psi	1,250	123	17,775
FLEXURAL MODULUS	73°F (23°C)	D790	kgf/cm ²	Mpa	psi	29,500	2,893	419,479
IZOD NOTCHED IMPACT STRENGTH		D256	kgcm/cm	J/m	ft.lb/in	5.0	49.0	0.9
HARDNESS ROCKWELL	R SCALE	D785	g/cc			125		
ELECTRICAL								
ARC RESISTANCE	D495	sec			128			
DIELECTRIC CONSTANT	D150	10 ⁶ Hz			3.4			
DIELECTRIC STRENGTH	D149	KV/mm			20			

The information provided on our present state of knowledge and is estimated by Kolon Industries Inc. The listed values should be used for referential purposed only. This information should not be used as guranteed specification limits.

Kolon industries Inc assumes no warranty, no obligations or liability of, express or implied aas to the accuracy or compeltteness thereof, or any other nature regarding designs, products, or information may be used without infringing the intellectual property rights of others. All such advice is given and accepted at buyer's risk.

API-KOLON
Engineering Plastics

333 Enterprise Parkway • Lake Zurich • IL • 60047 • USA

Phone: 1-847-550-5556 Fax: 1-847-550-5557

Email: MaxHahn21@hotmail.com