SPESIN®

KOLON PLASTIC BUSINESS TEAM

G/F reinforced, Flame retardant Grade

KP212G15V0N

PBT compounded resin, G/F 15% reinforced, flame retardant, easy printing grade

TEST ITEM		ASTM	UNIT	VALUE
Physical Property				
Specific Gravity	23℃	D792	-	**1.53**
Water Absorption		D570	%	**0.06**
Mold Shrinkage	23℃	D955	%	**0.6 - 1.4**
Mechanical Property				
Tensile Strength	23℃	D638	Kg/㎠	**950**
Tensile Elongation	23℃	D638	%	**7.0**
Flexural Strength	23℃	D790	Kg/㎠	**1,700**
Flexural Modulus	23℃	D790	Kg/㎠	**56,000**
Impact Strength (Izod Notch)	23℃	D256	Kg • cm/cm	**6.0**
Hardness (Rockwell)		D785	R scale	**119**
Thermal Property				
Melting Point		D789	℃	**224**
Coefficient of Linear Thermal Expansion		D696	cm/cm/℃(X10^{-4})	**0.4**
Heat Distortion Temperature		D648		
	4.6kg/㎠		℃	**215**
	18.6kg/㎠		℃	**178**
Flammability		UL94	UL 94	**V 0**
Electrical Property				
Arc Resistance	23℃	D495	sec	**120**
Dielectric Constant	23℃	D150	10^6 Hz	**3.5**
Dielectric Strength	23℃	D149	KV/mm	**26**

Remark: The information provided in this data sheet is based on Kolon's knowledge and test method, therefore it can not be used as guaranteed specification limits.

API-KOLON
Engineering Plastics

333 Enterprise Parkway • Lake Zurich • IL • 60047 • USA
Phone: 1-847-550-5556 Fax: 1-847-550-5557
Email: MaxHahn21@hotmail.com