

KP 213HB40BL

PBT compounded resin, G/F+M/F 40% reinforced,
Flame retardant & low distortion with black color

TEST ITEM		ASTM	UNIT	VALUE
Physical Property				
Specific Gravity	23°C	D792	-	1.55
Water Absorption		D570	%	0.06
Mold Shrinkage	23°C	D955	%	0.3 - 0.6
Mechanical Property				
Tensile Strength	23°C	D638	Kg/cm ²	1,000
Tensile Elongation	23°C	D638	%	4.7
Flexural Strength	23°C	D790	Kg/cm ²	1,700
Flexural Modulus	23°C	D790	Kg/cm ²	75,000
Impact Strength (Izod Notch)	23°C	D256	Kg • cm/cm	6.0
Hardness (Rockwell)		D785	R scale	119
Thermal Property				
Melting Point		D789	°C	224
Coefficient of Linear Thermal Expansion		D696	cm/cm/ °C(X10 ⁻⁴)	0.4
Heat Distortion Temperature		D648		
	4.6kg/cm ²		°C	220
	18.6kg/cm ²		°C	205
Flammability		UL94	UL 94	HB
Electrical Property				
Arc Resistance	23°C	D495	sec	110
Dielectric Constant	23°C	D150	10 ⁶ Hz	3.7
Dielectric Strength	23°C	D149	KV/mm	27

Remark: The information provided in this data sheet is based on Kolon's knowledge and test method, therefore it can not be used as guaranteed specification limits.

API-KOLON
Engineering Plastics

333 Enterprise Parkway • Lake Zurich • IL • 60047 • USA

Phone: 1-847-550-5556 Fax: 1-847-550-5557

Email: MaxHahn21@hotmail.com