

PROPERTY INFORMATION

KOLON INDUSTRIES INC

KOPET®
PET RESIN

KP132G30VO

FLAME RETARDANT WITH G/F GRADE

PROPERTY	ASTM METHOD	UNIT			VALUE			
MISCELLANEOUS								
SPECIFIC GRAVITY	D792				1.67			
WATER ABSORPTION	D570	%			0.05			
MOLD SHRINKAGE	D955	%			0.3			
THERMAL								
MELTING POINT	D789	°C	°F	254	489			
HEAT DISTORTION TEMPERATURE	D648							
4.6kg.f/cm ² (0.46 Mpa)		°C	°F	224	435			
COEFFICIENT OF LINEAR THERMAL EXPANSION	D696	10 ⁻⁴ cm/cm/°C			0.3			
FLAMMABILITY	UL94				V-O			
MECHANICAL								
TENSILE STRENGTH	73°F (23 °C)	D638	kgf/cm ²	Mpa	psi	1,350	132	19,197
TENSILE ELOGATION	73°F (23 °C)	D638	%			5		
FLEXURAL STRENGTH	73°F (23 °C)	D790	kgf/cm ²	Mpa	psi	2,300	226	32,705
FLEXURAL MODULUS	73°F (23 °C)	D790	kgf/cm ²	Mpa	psi	100,000	9,807	1,421,964
IZOD NOTCHED IMPACT STRENGTH		D256	kgcm/cm	J/m	ft.lb/in	7.5	74	1.38
HARDNESS ROCKWELL	R SCALE	D785	g/cc			120		
ELECTRICAL								
ARC RESISTANCE	D495	sec			100			
DIELECTRIC CONSTANT	D150	10 ⁶ Hz			3.7			
DIELECTRIC STRENGTH	D149	KV/mm			20			

The information provided on our present state of knowledge and is estimated by Kolon Industries Inc. The listed values should be used for referential purposed only. This information should not be used as guaranteed specification limits.

Kolon industries Inc assumes no warranty, no obligations or liability of, express or implied aas to the accuracy or compelteness thereof, or any other nature regarding designs, products, or information may be used without infringing the intellectual property rights of others. All such advice is given and accepted at buyer's risk.

API-KOLON
Engineering Plastics

1121 Rose Road • Lake Zurich • IL • 60047 • USA
Phone: 1(847)550-5556 Fax: 1(847)550-5557
Email: MaxHahn21@hotmail.com